

Attenuation Grade **TiO₂ Dispersions**

Titanium Dioxide (TiO₂) is a well known pigment, because of its high refractive index. It also functions as an effective UV absorber when the primary particle size is under 100 nm. Titanium Dioxide is ideal for formulating mild or hypoallergenic sun care products for UVA/UVB protection for babies and children, and consumers with sensitive skin. It's the physical and chemical stability of titanium dioxide, which differentiates this filter from organic UV absorbers.


Titanium Dioxide is available in a wide range of primary particle sizes and varying optical properties. However, Titanium Dioxide is not supplied as individual crystals, but as aggregates of primary

particles. The degree of aggregation is a function of the primary particle size and manufacturing process. These large aggregates may reduce the protection of the formula against UV light, and likewise scatter visible light, sometimes creating an ashy look when sun care products are applied on skin.

Kobo specializes in the custom formulation and dispersion of TiO₂. We offer a wide selection of Titanium Dioxide dispersions that include various particle sizes, surface treatments, and a wide range of carriers, including volatile solvent bases. Kobo can also provide formulation assistance based on our extensive experience formulating and testing sunscreen products containing inorganic UV filters.



There is a wide range of TiO₂ available with different primary particle sizes (PPS). These pictures compare the transparency of TiO₂ dispersions (at 20% concentration) of various PPS on two different skin types. The small primary particle size Titanium Dioxide dispersion shows high transparency and is also likely to be efficient against UVB light.



This figure shows transmittance curves. The curves show the relationship not only between particle size and transparency, but also between particle size and UVA/UVB balance. As the particle size becomes very small, UVB attenuation is strong but UVA attenuation is weak. The Titanium Dioxide particle size must be in a medium range if balanced protection in both the UVA and UVB regions is desired.

W/O Milky Sunscreen with TNP50T7-ATB

Formula KSL-280A

Part 1

- KF-995 - Shin Etsu: *Cyclopentasiloxane* 33.00%
- **TNP50T7-ATB** - Kobo Products: *C12-15 Alkyl Benzoate (And) Titanium Dioxide (And) Argania Spinosa Kernel Oil (And) Alumina (And) Hydrogen Dimethicone (And) Tocopheryl Acetate (And) Polyhydroxystearic Acid (And) Bisabolol* 18.03%
- KF-6040 - Shin Etsu: *Cyclopentasiloxane (And) PEG/PPG-18/18 Dimethicone* 3.60%
- Abil® EM 90 - Evonik: *Cetyl PEG/PPG-10/1 Dimethicone* 2.00%
- ELEMENT14 PDMS 20 - Momentive: *Dimethicone* 2.00%
- SF1528 - Momentive: *Cyclopentasiloxane (And) PEG/PPG-20/15 Dimethicone* 0.75%
- **CXG-1101** - NuSil/Kobo Products: *Cyclopentasiloxane (And) Dimethicone/Vinyl Dimethicone Crosspolymer* 0.70%

Part 2

- Deionized Water - *Water* 31.52%
- Butylene Glycol - Ruger Chemical: *Butylene Glycol* 2.80%
- Glycerin U.S.P. Natural 96% - Ruger Chemical: *Glycerin* 1.50%
- Sodium Chloride - Morton Salt: *Sodium Chloride* 0.75%
- Magnesium Sulphate - Mallinckrodt: *Magnesium Sulfate* 0.60%
- Liposorb® L-20 - Vantage: *Polysorbate 20* 0.30%
- Phenoxyethanol - Clariant: *Phenoxyethanol* 0.15%
- ALLANTOIN - ISP: *Allantoin* 0.10%

- Methyl Paraben NF - International Sourcing: *Methylparaben* 0.10%
- Trisodium EDTA - Protameen: *Trisodium EDTA* 0.10%

Part 3

- **MSS-500W** - Kobo Products: *Silica* 2.00%

Manufacturing Procedure

1. Combine all Part 1 ingredients and homogenize until fully dispersed.
 2. Combine all Part 2 ingredients and homogenize until fully dispersed.
 3. Slowly add Part 2 to Part 1 while homogenizing until homogeneous.
 4. Slowly add Part 3 while homogenizing until fully dispersed.
- Note: This procedure is cold process.

Description

This sunscreen features Kobo's Titanium Dioxide Dispersion TNP50T7-ATB, an optimized mixture of a TiO₂ sunscreen dispersion with Kobo's Sunboost ATB™, that is a proprietary blend of antioxidants, anti-irritant and anti-inflammatory agents. CXG-1101 imparts a creamy, gel texture to the product, and MSS-500W gives a creamy slip during application.

in vivo SPF 27.5
in vivo UVA-PF 8.70
CW 373

KOBO

Kobo Products, Inc.
3474 So. Clinton Ave.
So. Plainfield, NJ 07080
USA
tel +1 (908) 757-0033
fax +1 (908) 757-0905

Kobo Products, SAS
135 Rue Buissonniere
Quartier Bouysset
31670 LABEGE
France
tel +33 (0)5-62-88-77-40
fax +33 (0)5-62-88-77-49

Kobo Dispatel, Inc.
1 - 4 - 8
Nihombashi-bakurocho
Chuoku, Tokyo, 103-0002
Japan
tel +81 (3) 3663-8049
fax +81 (3) 3664-8679

Kobo Brasil Ltda.
Rua Bamboaré n.41
Ipiranga - São Paulo/SP
04278-060
Brasil
tel +55 (11) 5062-0634

TiO₂ Dispersions

Carrier/ Solvent	Product Name	INCI Name	Primary Part. Size (nm)	Particle Size** (nm)	Active %	Viscosity
Silicones	CM3K40T4*	Cyclopentasiloxane (And) Titanium Dioxide (And) PEG-10 Dimethicone (And) Alumina (And) Hydrogen Dimethicone	15	120	33	pourable
	<small>New</small> CMF655T4*	Titanium Dioxide (And) Cyclopentasiloxane (And) Polyglyceryl-3 Polydimethylsiloxyethyl Dimethicone (And) Alumina (And) Hydrogen Dimethicone	15	155	44	pourable
Mixed Solvents	KFS40M170*	Caprylyl Methicone (And) Titanium Dioxide (And) Cyclopentasiloxane (And) C12-15 Alkyl Benzoate (And) Alumina (And) Polyhydroxystearic Acid (And) Hydrogen Dimethicone (And) PEG-9 Polydimethylsiloxyethyl Dimethicone	14	150	32	pourable
	HBTNP60TV*	Butyloctyl Salicylate (And) Titanium Dioxide (And) Stearic Acid (And) Aluminum Hydroxide (And) C12-15 Alkyl Benzoate (And) Polyhydroxystearic Acid	15	112	50	paste
	<small>New</small> HBTN55TIS-EU*	Butyloctyl Salicylate (And) Titanium Dioxide (And) Isostearic Acid (And) Aluminum Hydroxide (And) C12-15 Alkyl Benzoate (And) Stearic Acid	15	110-150	44	paste
Esters/Oils	TNP50M170*	C12-15 Alkyl Benzoate (And) Titanium Dioxide (And) Alumina (And) Hydrogen Dimethicone (And) Polyhydroxystearic Acid	14	125	39	pourable
	GCP50M170*	Caprylic/Capric Triglyceride (And) Titanium Dioxide (And) Alumina (And) Polyhydroxystearic Acid (And) Hydrogen Dimethicone	14	125	39	pourable
	HBP50T7*	Butyloctyl Salicylate (And) Titanium Dioxide (And) Alumina (And) Hydrogen Dimethicone (And) Polyhydroxystearic Acid	15	114	39	pourable
	TNP50T7-ATB*	C12-15 Alkyl Benzoate (And) Titanium Dioxide (And) Argania Spinosa Kernel Oil (And) Alumina (And) Hydrogen Dimethicone (And) Tocopheryl Acetate (And) Polyhydroxystearic Acid (And) Bisabolol	15	118	38	pourable
	OMP50T7*	Octyldodecyl Myristate (And) Titanium Dioxide (And) Alumina (And) Polyhydroxystearic Acid (And) Hydrogen Dimethicone	15	119	40	pourable
	TNP50T7*	C12-15 Alkyl Benzoate (And) Titanium Dioxide (And) Alumina (And) Polyhydroxystearic Acid (And) Hydrogen Dimethicone	15	120	40	pourable
	IN60TIS	Titanium Dioxide (And) Isononyl Isononanoate (And) Isostearic Acid (And) Aluminum Hydroxide	15	120	48	paste
	INP60T7*	Titanium Dioxide (And) Isononyl Isononanoate (And) Alumina (And) Hydrogen Dimethicone (And) Polyhydroxystearic Acid	15	126	48	pourable
	HBP45M160	Butyloctyl Salicylate (And) Titanium Dioxide (And) Alumina (And) Stearic Acid (And) Polyhydroxystearic Acid	17	192	36	pourable
	TNQP55T5S*	C12-15 Alkyl Benzoate (And) Titanium Dioxide (And) Stearic Acid (And) Aluminum Hydroxide (And) Polyhydroxystearic Acid	30	168	45	paste
	<small>New</small> INQP70TMD*	Titanium Dioxide (And) Isononyl Isononanoate (And) Polyhydroxystearic Acid (And) Hydrogen Dimethicone (And) Dimethicone	35	163	64	pourable
TNQP50TEL6*	C12-15 Alkyl Benzoate (And) Titanium Dioxide (And) Alumina (And) Silica (And) Polyhydroxystearic Acid	50	190	44	pourable	
Natural Esters/Oils	JOSP50TJE*	Simmondsia Chinensis (Jjoba) Seed Oil (And) Titanium Dioxide (And) Aluminum Hydroxide (And) Jojoba Esters (And) Polyhydroxystearic Acid	15	128	39	paste
	JOSP40TIS	Simmondsia Chinensis (Jjoba) Seed Oil (And) Titanium Dioxide (And) Aluminum Hydroxide (And) Isostearic Acid (And) Polyhydroxystearic Acid	15	130	33	pourable
	GCO45TV*	Titanium Dioxide (And) Caprylic/Capric Triglyceride (And) Sorbitan Olivate (And) Stearic Acid (And) Aluminum Hydroxide	15	131	38	paste
	GCP55TJ*	Titanium Dioxide (And) Caprylic/Capric Triglyceride (And) Jojoba Esters (And) Polyhydroxystearic Acid	35	139	52	paste
	GCQP55T5S*	Caprylic/Capric Triglyceride (And) Titanium Dioxide (And) Stearic Acid (And) Aluminum Hydroxide (And) Polyhydroxystearic Acid	35	161	45	pourable
Aqueous <small>New</small>	WBG40TWP*	Water (And) Titanium Dioxide (And) Butylene Glycol (And) Hydrated Silica (And) Ammonium Polyacrylate	15	188	28	pourable

This table was prepared to assist in formulating with Titanium Dioxide Dispersions. The information contained herein is believed to be accurate at the time of printing and represent typical values, but should not be used as a substitute for product specification sheets.

*These TiO₂ products comply with the conditions for Titanium Dioxide (nano) as set forth in the Annex VI to Regulation (EC) No 1223/2009.

**Size in dispersion: intensity-weighted mean size measured on Dynamic Light Scattering particles sizer

Kobo also offers Dispersions in Volatile Non-D5 Carriers. Please see separate flyer.

Our dispersions are often divided into two general categories:

- High Solids® Dispersions:** These are usually in paste form and have a high active TiO₂ loading and efficacy (up to 5 SPF units/ TiO₂%), which is necessary for formulating for very high SPF.
- High Speed™ Dispersions:** These are usually pourable and easy to incorporate into a formulation. They are highly transparent.

Formulation guidelines

estimation of use level for SPF

10 -15 nm TiO₂ Dispersions

- SPF < 20 : 2.0-2.5 SPF / % TiO₂
- SPF > 25 : 2.5-3.0 + SPF / % TiO₂