


# Microspheres

## Latin America Program




**Microspheres** are discrete spherical particles ranging from 1 to 50 microns in average particle size. Depending on their size and composition, Microspheres will impart finished products with elegant **silky textures**, **enhanced slip** or **ball bearing effect**; they will promote better blendability on the skin, a more natural finish and increased payoff. Microspheres are also able to scatter light to diminish the look of fine lines on the skin, while letting enough light through so the look of the skin is natural, an effect known as “**Soft Focus**” or “**Optical Blurring.**” Some Microspheres are porous and have a high **oil absorption capacity**: they can be used for sebum


control or as carriers to absorb and deliver materials. A special use of Microspheres is in mascaras: non-absorbent grades of silicas of different diameters have a **volumizing effect**, with minimum absorbency.

Kobo offers a wide range of Microspheres, with different sizes, feel, absorption, and composition which allow formulators achieve the effects they need in their formulas.


Kobo also offers Surface Treated Microspheres, Microsphere Complexes and Composite Microspheres, which can be used instead of, or in combination with, regular Microspheres to achieve unique effects (*download or request flyers*).



MSS-500W



SILICA SHELLS



FLORITE PS-10



KLP-162

## High Coverage, Semi-Matte Lipstick

### Part 1

- **INBP45R7C** - Kobo Products: *Red 7 Lake (And) Isononyl Isononanoate (And) Isopropyl Myristate (And) Stearalkonium Hectorite (And) Isopropyl Titanium Triisostearate (And) Propylene Carbonate (And) Polyhydroxystearic Acid* 14.00%
- **COSMOL™ 222** - Ikeda Corporation: *Diisostearyl Malate* 13.20%
- **COSMOL™ 168ARV** - Ikeda Corporation: *Dipentaerythryl Hexahydroxystearate/Hexastearate/Hexarosinate* 10.52%
- **COSMOL™ 43V** - Ikeda Corporation: *Polyglyceryl-2 Triisostearate* 10.00%
- **KOBOGUARD® 5400 CCT** - Kobo Products: *Hydrogenated Polycyclopentadiene (And) Caprylic/Capric Triglyceride* 10.00%
- **CPF-3300@10cSt** - Avantor/Kobo Products: *Phenyl Trimethicone* 7.98%
- **INBP70U** - Kobo Products: *Titanium Dioxide (And) Isononyl Isononanoate (And) Isopropyl Myristate (And) Stearalkonium Hectorite (And) Isopropyl Titanium Triisostearate (And) Propylene Carbonate (And) Polyhydroxystearic Acid* 7.00%
- **Ozokerite Wax White SP 1020P** - Strahl & Pitsch: *Ozokerite* 6.00%
- **PM WAX 82** - Toray/Kobo Products: *Polyethylene (And) Microcrystalline Wax* 4.90%

- **INBP55EY** - Kobo Products: *Iron Oxides (CI 77492) (And) Isononyl Isononanoate (And) Isopropyl Myristate (And) Stearalkonium Hectorite (And) Polyhydroxystearic Acid (And) Isopropyl Titanium Triisostearate (And) Propylene Carbonate* 4.40%
- **CARESS® BN30** - Bent Tree/Kobo Products: *Boron Nitride* 4.00%
- **SALACOS® 334** - Ikeda Corporation: *Caprylic/Capric/Myristic/Stearic Triglyceride* 2.00%

### Part 2

- **MSS-500/3H** - Kobo Products: *Silica* 4.00%
- **SILICA SHELLS** - Kobo Products: *Silica* 2.00%

### Manufacturing Procedure

1. Combine Part 1 and heat to 85 °C.
2. Slowly add Part 2 and mix until homogeneous.
3. Pour at 85 °C (ensure lipstick mold is not cold).

### Description

This high coverage, semi-matte lipstick features a combination of Kobo's high oil absorption microspheres, **SILICA SHELLS** and **MSS-500/3H**, which offer a background matte effect with increased payoff and a smooth application. CARESS® BN30 is a boron nitride that improves wear and gives a velvet finish. Kobo's INBP Pigmentary Dispersions ease the manufacturing process and give a more intense, uniformly developed color. CPF-3300@10cSt is a low viscosity phenyl trimethicone that improves feel and application. PM WAX 82 contributes to the structure of the formula. KOBOGUARD® 5400 CCT is a film former that helps with long wear.

**KOBO**

USA

BRASIL

UK

FRANCE

ASIA PACIFIC

	Trade Name	INCI Name	Size (µm)	Oil Abs* (g/100g)	Refract Index	Bulk Density (g/in <sup>3</sup> )
Natural Origin	<b>New</b> KOBOSPHERE™ NATURAL BBS-ASG4	<i>Amylopectin (And) Stearoyl Glutamic Acid</i>	10	35	1.535	6.5
	<b>New</b> MC Powder	<i>Chitin</i>	15	96	N/A	2.42
	<b>New</b> SP-500-MD	<i>Caprolactone/Pyrrrolidone Copolymer</i>	7	65	N/A	N/A
Mineral Microspheres	<b>New</b> EXCEBEADS™ CS-320	<i>Silica</i>	3.5	24	1.47	9.55
	<b>New</b> EXCEBEADS™ CS-725		7	22	1.47	11.27
	MSS-500/3		3	135	1.47	3.5
	MSS-500/3H		3	300	1.47	1.3
	MSS-500/5H		5	300	1.47	2.5
	MSS-500/3N		3	33	1.47	6.1
	MSS-500		12	133	1.47	5.8
	MSS-500W <b>C</b>		12	119	1.47	6.2
	<b>New</b> MSS-500W/H		9	250	1.47	3.05
	MSS-500/H		12	300	1.47	3.1
	MSS-500/N		12	38	1.47	6.7
	MSS-500/20N		20	40	1.47	12.9
	SILICA SHELLS		3	490	1.47	0.8
	FLORITE PS-10 C-GRADE		10	434	1.63	1.1
FLORITE R C-GRADE	29	650	1.63	1.2		
Polymer Microspheres	MST-203	<i>Polymethylsilsesquioxane</i>	2	50	1.41	6.5
	MST-547		4.5	54	1.41	7.0
	Diasphere® KS-500C		5	96	1.41	7.0
	Diasphere® KS-1000C		10	50	1.41	5.0
	GWC-060F	<i>Polybutyl Methacrylate</i>	6	55	1.48	5.0
	LSP-537	<i>Methyl Methacrylate Crosspolymer</i>	5	71	1.49	3.8
	MSP-930		7	59	1.49	6.4
	MSP-825		8	57	1.49	6.7
	MSP-822		9	48	1.49	5.3
	GWC-150E	<i>Polybutyl Acrylate (And) Silica</i>	15	65	1.49	8.0
	BPD-500W	<i>HDI/Trimethylol Hexyllactone Crosspolymer (And) Silica</i>	11	60	1.52	8.2
	SP-500	<i>Nylon-12</i>	5	60	1.53	4.7
	SP-10		10	60	1.53	6.2
	GWC-060G	<i>Styrene/Acrylates Copolymer</i>	6	55	1.54	4.1
Spherical Elastomers	GWC-051H	<i>Vinyl Dimethicone/Methicone Silsesquioxane Crosspolymer</i>	5	80	1.41	2.9
	MST-E8		8	77	1.41	4.1

\* Oil Abs: ASTM, D281-84

This chart was prepared to assist in formulating with Microspheres. The information contained herein is believed to be accurate at the time of printing, but should not be used as a substitute for product specification sheets.



**C** Raw materials approved by COSMOS