



KEY-138

# Talc-Free Pressed Powder Eyeshadow

%	INGREDIENT	INCI NAME	SUPPLIER
<b>Part 1</b>			
32.50	<b>FSL-CSO-NJE5</b>	Calcium Starch Octenylsuccinate (And) Mica (And) Jojoba Esters	<b>Kobo Products</b>
12.00	<b>KoboMica S-25</b>	Mica	<b>Kobo Products</b>
10.00	ZINC STEARATE	Zinc Stearate	Strahl & Pitch
9.00	<b>CARESS® BN06</b>	Boron Nitride	<b>Kobo Products</b>
4.67	<b>BWBO-ASGP3</b>	Iron Oxides (CI 77499) (And) Stearoyl Glutamic Acid (And) Polyhydroxystearic Acid	<b>Kobo Products</b>
3.13	<b>BWRO-ASGP3</b>	Iron Oxides (CI 77491) (And) Stearoyl Glutamic Acid (And) Polyhydroxystearic Acid	<b>Kobo Products</b>
2.20	<b>BWYO-ASGP3</b>	Iron Oxides (CI 77492) (And) Stearoyl Glutamic Acid (And) Polyhydroxystearic Acid	<b>Kobo Products</b>
<b>Part 2</b>			
14.00	<b>KTZ® MISTERIOSO BRONZE-I2</b>	Mica (And) Iron Oxides (CI 77491) (And) Iron Oxides (CI 77499) (And) Isopropyl Titanium Trisostearate	<b>Kobo Products</b>
8.00	<b>KTZ® BRONZE-11S2</b>	Mica (And) Iron Oxides (CI 77491) (And) Triethoxycaprylylsilane	<b>Kobo Products</b>
<b>Part 3</b>			
2.00	Protachem CTG	Caprylic/Capric Triglyceride	Protameen Chemicals
2.00	EUTANOL G	Octyldodecanol	BASF
0.50	Jeecide Cap-7	Caprylyl Glycol (and) Glyceryl Laurate (and) Glyceryl Undecylenate	Jeen International Corporation
<b>100.00</b>			

## Description:

A pressed powder eyeshadow with a beautiful metallic shimmer finish. FSL-CSO-NJE5 is Kobo's talc replacement that has many of the same great properties as talc. KoboMica S-25 gives the formula a smooth and soft feel, excellent spreadability, and superb skin adhesion. CARESS® BN06 is used for superior softness and tactility, superb spreadability, excellent adherence, and great coverage. The ASGP3 pigments are natural and coated with a hybrid treatment that renders powders hydrophobic and super dispersible. They give a creamy feel on the skin and promote skin adhesion in pressed powders. KTZ® Mysterioso Bronze-I2 & KTZ® Bronze-11S2 are free flowing brown powders that have a bronze reflection color.

## Manufacturing Procedure:

1. Blend Part 1 at the highest speed for 1 minute.
2. Combine Part 1&2 and mix for 30 seconds.
3. Add Part 3 and mix for 30 seconds. Scrape the sides of the vessel and blade and then mix again for 30 seconds.
4. Fill weight is 3.50g - 4.50 g. Press at 600 PSI.



**KOBO**  
www.koboproducts.com

October, 2022

## FORMULATIONS

Product formulations are included as illustrative examples only. Kobo Products Inc. makes no representation or warranty concerning the efficacy or safety of any product manufactured using such formulations. All statements concerning the possible use of Kobo Products Inc. are for research purposes only. Responsibility for the performance or adequate testing of any product prior to sale or use of any such product lies with the manufacturer thereof.

## USE OF PRODUCTS

Products sold by Kobo are designed, manufactured and sold for industrial use only. Prior to use of any such product for any application other than an industrial use, the user has the sole responsibility and obligation to determine the suitability of any such product for any such application.

## PATENT STATUS

Nothing contained herein shall be construed to imply the nonexistence of any relevant patents or to constitute a permission, inducement or recommendation to practice any invention covered by any patent, without authority from the owner of the patent.

## LIMITATION OF LIABILITY

Kobo Products Inc. shall in no event, whether the claim is based on warranty, contract, tort, strict liability, negligence or otherwise, be liable for incidental or consequential damages, or for any other damages in excess of the amount of the purchase price.

# KOBO

## *The Powder & Dispersion Specialist*



**KOBO PRODUCTS, INC**  
3474 South Clinton Avenue  
South Plainfield, NJ 07080  
USA

Tel: +1 - 908 757 0033  
Fax: +1 - 908 757 0905



**KOBO BRASIL, LTDA**  
Rua Francisco Nakazato n. 2357  
Itupeva SP 13.295-000  
BRASIL

Tel: +55 (11) 5062 6034



**KOBO PRODUCTS, LTD**  
67D(IV), Innovation Drive  
Milton Park, Abingdon, OX14 4RQ  
UNITED KINGDOM

Tel: +44 7913 636 673



**KOBO PRODUCTS, SAS**  
135 Rue Buissonnière  
Quartier Bouysset  
31670 Labège  
FRANCE

Tel: +33 - (0) 5 62 88 77 40  
Fax: +33 - (0) 5 62 88 77 49



**KOBO DISPATEK, INC**  
1-4-8 Nihombashi-bakurocho  
Chuoko, Tokyo, 103-0002  
JAPAN

Tel: +81 - 3 3663 8049  
Fax: +81 - 3 3661 8679

[www.koboproducts.com](http://www.koboproducts.com)