



KLP-200

Lipstick To Impress

%	INGREDIENT	INCI NAME	SUPPLIER
Part 1			
19.80	Castor Oil	Ricinus Communis (Castor) Seed Oil	Arista Industries, Inc.
12.00	Softisan® 645	Bis-Diglyceryl Polyacyladipate-1	IOI Oleo GmbH
11.00	Wickenol 155	Ethylhexyl Palmitate	Alzo International Inc.
6.00	KOBOGUARD® 5400 CCT	Hydrogenated Polycyclopentadiene (And) Caprylic/Capric Triglyceride	Kobo Products
6.00	Candelilla Wax SP 75	Euphorbia Cerifera (Candelilla) Wax	Strahl & Pitsch
4.50	Ozokerite Wax White SP 1020	Ozokerite	Strahl & Pitsch
3.00	Lipowax® D	Cetearyl Alcohol (And) Ceteareth-20	Vantage
2.50	Shea Butter	Shea Butter	BASF
2.00	Microcrystalline Wax SP-89	Microcrystalline Wax	Strahl & Pitsch
1.00	MSS-500/3H	Silica	Kobo Products
0.10	Propyl Paraben NF	Propylparaben	International Sourcing
0.10	BHT Food Grade Crystal	BHT	Protameen
Part 2			
16.00	INWP75ER	Iron Oxides (CI 77491) (And) Isononyl Isononanoate (And) Ozokerite (And) Isopropyl Titanium Triisostearate (And) Polyhydroxystearic Acid	Kobo Products
16.00	INWP45R7C	Red 7 Lake (And) Isononyl Isononanoate (And) Ozokerite (And) Isopropyl Titanium Triisostearate (And) Polyhydroxystearic Acid	Kobo Products
100.00			

Description:

This lipstick has bright, rich color, high coverage and feels very smooth, soft, creamy and comfortable on the lips. This dense formula contains Kobo's INWP Pigmentary Dispersions which disperse easily into lipstick bases and help to achieve a high impact of color in formulations. MSS-500/3H enhances payoff and prevents the formula from sweating. KOBOGUARD® 5400 CCT gives gloss to the formula and improves long

Manufacturing Procedure:

1. Combine Part 1 under propeller mixing and heat to 80°C-85°C.
2. Add Part 2 to Part 1 and mix until homogeneous.
4. Pour into molds at 78°C - 80°C.



KOBO
www.koboproducts.com

September, 2018

FORMULATIONS

Product formulations are included as illustrative examples only. Kobo Products Inc. makes no representation or warranty concerning the efficacy or safety of any product manufactured using such formulations. All statements concerning the possible use of Kobo Products Inc. are for research purposes only. Responsibility for the performance or adequate testing of any product prior to sale or use of any such product lies with the manufacturer thereof.

USE OF PRODUCTS

Products sold by Kobo are designed, manufactured and sold for industrial use only. Prior to use of any such product for any application other than an industrial use, the user has the sole responsibility and obligation to determine the suitability of any such product for any such application.

PATENT STATUS

Nothing contained herein shall be construed to imply the nonexistence of any relevant patents or to constitute a permission, inducement or recommendation to practice any invention covered by any patent, without authority from the owner of the patent.

LIMITATION OF LIABILITY

Kobo Products Inc. shall in no event, whether the claim is based on warranty, contract, tort, strict liability, negligence or otherwise, be liable for incidental or consequential damages, or for any other damages in excess of the amount of the purchase price.

KOBO

The Powder & Dispersion Specialist



KOBO PRODUCTS, INC
3474 South Clinton Avenue
South Plainfield, NJ 07080
USA

Tel: +1 - 908 757 0033
Fax: +1 - 908 757 0905



KOBO BRASIL, LTDA
Rua Francisco Nakazato n. 2357
Itupeva SP 13.295-000
BRASIL

Tel: +55 (11) 5062 6034



KOBO PRODUCTS, LTD
67D(IV), Innovation Drive
Milton Park, Abingdon, OX14 4RQ
UNITED KINGDOM

Tel: +44 7913 636 673



KOBO PRODUCTS, SAS
135 Rue Buissonnière
Quartier Bouysset
31670 Labège
FRANCE

Tel: +33 - (0) 5 62 88 77 40
Fax: +33 - (0) 5 62 88 77 49



KOBO DISPATEK, INC
1-4-8 Nihombashi-bakurocho
Chuoko, Tokyo, 103-0002
JAPAN

Tel: +81 - 3 3663 8049
Fax: +81 - 3 3661 8679

www.koboproducts.com

www.koboproducts.com