



KPP-127D

Natural, Talc-free Pressed Powder

%	INGREDIENT	INCI NAME	SUPPLIER
Part 1			
44.68	GMS-NOE4	Mica (And) Hydrogenated Olive Oil Stearyl Esters	Kobo Products
40.00	FSL-CSO-NJE5	Calcium Starch Octenylsuccinate (And) Mica (And) Jojoba Esters	Kobo Products
7.00	BTD-NOE2	Titanium Dioxide (And) Hydrogenated Olive Oil Stearyl Esters	Kobo Products
1.00	BRO-NOE4	Iron Oxides (CI 77491) (And) Hydrogenated Olive Oil Stearyl Esters	Kobo Products
0.86	BYO-NOE4	Iron Oxides (CI 77492) (And) Hydrogenated Olive Oil Stearyl Esters	Kobo Products
0.46	BBO-NOE4	Iron Oxides (CI 77499) (And) Hydrogenated Olive Oil Stearyl Esters	Kobo Products
Part 2			
5.50	OLIVE OIL (PURE)	OLEA EUROPAEA (Olive Fruit) OIL (PURE)	Jeen International
0.50	Lexgard® Natural	Glyceryl Caprylate (And) Glyceryl Undecylenate	Inolex
100.00			

Description:

This light-as-air, natural pressed powder can be used on multiple complexions to even out skin tone. The use of Kobo's pigments and filler treated with Natural Olive Esters (NOE) provides a creamy feel and improves pressability. Powders can be pressed without additional dry binders when using NOE treated pigments. FSL-CSO-NJE5 is a talc alternative that improves skin adhesion and contributes to the elegant texture.

Manufacturing Procedure:

1. Combine Part 1 and blend on high speed until pigments are uniform.
2. Add Part 2 to Part 1 and blend on high speed until oil is dispersed.
3. Press at 1000 psi.



KOBO
www.koboproducts.com

December, 2022

FORMULATIONS

Product formulations are included as illustrative examples only. Kobo Products Inc. makes no representation or warranty concerning the efficacy or safety of any product manufactured using such formulations. All statements concerning the possible use of Kobo Products Inc. are for research purposes only. Responsibility for the performance or adequate testing of any product prior to sale or use of any such product lies with the manufacturer thereof.

USE OF PRODUCTS

Products sold by Kobo are designed, manufactured and sold for industrial use only. Prior to use of any such product for any application other than an industrial use, the user has the sole responsibility and obligation to determine the suitability of any such product for any such application.

PATENT STATUS

Nothing contained herein shall be construed to imply the nonexistence of any relevant patents or to constitute a permission, inducement or recommendation to practice any invention covered by any patent, without authority from the owner of the patent.

LIMITATION OF LIABILITY

Kobo Products Inc. shall in no event, whether the claim is based on warranty, contract, tort, strict liability, negligence or otherwise, be liable for incidental or consequential damages, or for any other damages in excess of the amount of the purchase price.

KOBO

*The Powder & Dispersion
Specialist*



KOBO PRODUCTS, INC
3474 South Clinton Avenue
South Plainfield, NJ 07080
USA

Tel: +1 - 908 757 0033
Fax: +1 - 908 757 0905



KOBO BRASIL, LTDA
Rua Francisco Nakazato n. 2357
Itupeva SP 13.295-000
BRASIL

Tel: +55 (11) 5062 6034



KOBO PRODUCTS, LTD
67D(IV), Innovation Drive
Milton Park, Abingdon, OX14 4RQ
UNITED KINGDOM

Tel: +44 7913 636 673



KOBO PRODUCTS, SAS
135 Rue Buissonnière
Quartier Bouysset
31670 Labège
FRANCE

Tel: +33 - (0) 5 62 88 77 40
Fax: +33 - (0) 5 62 88 77 49



KOBO DISPATEK, INC
1-4-8 Nihombashi-bakurocho
Chuoko, Tokyo, 103-0002
JAPAN

Tel: +81 - 3 3663 8049
Fax: +81 - 3 3661 8679

www.koboproducts.com